

E/H (Ta2N) (Military M/D55342)

www.vishay.com


Vishay Dale Thin Film

QPL MIL-PRF-55342 Qualified Ta₂N Thin Film Resistor, Surface Mount Chip



Thin Film MIL chip resistors feature an all sputtered wraparound termination for excellent adhesion and dimensional uniformity. They are ideal in applications requiring stringent performance requirements. Established reliability is assured through 100 % screening and extensive environmental lot testing.

CONSTRUCTION



FEATURES

- Established reliability, "R" and "U" failure rate level (0.01 % per 1000 h), C = 2
- · High purity alumina substrate
- Wraparound termination featuring a tenacious adhesion layer covered with an electroplated nickel barrier layer for +150 °C operating conditions
- Very low noise and voltage coefficient (< -25 dB, 0.5 ppm/V)
- Non-inductive
- Laser-trimmed tolerances ± 0.1 %
- Complete MIL-testing available in-house
- Antistatic waffle pack or tape and reel packaging available
- Military / aerospace / QPL approval

TYPICAL PERFORMANCE

	ABSOLUTE
TCR	25
TOL.	0.1

STANDARD ELECTRICAL SPECIFICATIONS				
TEST	SPECIFICATIONS CONDITIONS			
Material	Tantalum nitride (Ta ₂ N) resistor film	-		
Resistance Range	49.9 Ω to 3.3 MΩ	-		
TCR: Absolute	± 25 ppm/°C to ± 300 ppm/°C	-55 °C to +125 °C		
Tolerance: Absolute	± 0.1 % to ± 10 %	+25 °C		
Stability: Absolute	$\Delta R \pm 0.02 \%$	2000 h at +70 °C		
Stability: Ratio	-	-		
Voltage Coefficient	0.1 ppm/V	-		
Working Voltage	30 V to 200 V	-		
Operating Temperature Range	-55 °C to +150 °C	-		
Storage Temperature Range	-55 °C to +150 °C	-		
Noise	< - 25 dB	-		
Shelf Life Stability: Absolute	ΔR ± 0.01 %	1 year at +25 °C		

COMPONENT RATINGS						
	POWER	WORKING	RESISTANCE RANGE BY TOLERANCE			
CASE SIZE	RATING (mW)		0.1 %, 0.25 %, 0.5 %, 1 %	2.0 % and 5.0 %	10 %	
M55342/01	50	40	49.9 Ω to 64.9 kΩ	51 Ω to 68 k Ω	51 Ω to 68 kΩ	
M55342/02	125	40	49.9 Ω to 140 kΩ	51 Ω to 150 k Ω	51 Ω to 150 kΩ	
M55342/03	200	75	49.9 Ω to 357 kΩ	51 Ω to 360 k Ω	51 Ω to 360 kΩ	
M55342/04	150	125	49.9 Ω to 806 kΩ	51 Ω to 820 k Ω	51 Ω to 820 kΩ	
M55342/05	225	175	49.9 Ω to 1.5 M Ω	51 Ω to 1.5 M Ω	51 Ω to 1.5 MΩ	
M55342/06	150	50	49.9 Ω to 309 kΩ	51 Ω to 820 k Ω	51 Ω to 820 kΩ	
D55342/07	250	100	49.9 Ω to 1 MΩ	51 Ω to 1 M Ω	51 Ω to 1 M Ω	
M55342/08	800	150	49.9 Ω to 2.0 M Ω	49.9 Ω to 2.0 M Ω	51 Ω to 2.23 MΩ	
M55342/09	1000	200	49.9 Ω to 3.01 MΩ	51 Ω to 3 M Ω	51 Ω to 3.3 MΩ	
M55342/10	500	75	49.9 Ω to 604 kΩ	51 Ω to 620 kΩ	51 Ω to 680 kΩ	
M55342/11	50	30	49.9 Ω to 49.9 kΩ	51 Ω to 51 kΩ	51 Ω to 51 kΩ	
M55342/12	100	50	49.9 Ω to 130 kΩ	51 Ω to130 k Ω	51 Ω to 150 k Ω	

Note

· Values listed are a guide, refer to MIL spec for value/tolerance allowance




E/H (Ta2N) (Military M/D55342)

www.vishay.com

Vishay Dale Thin Film

DIMENSIONS in inches



CASE SIZE	TERM.	L	W	Т	D	E
M55342/01	В	0.055 ± 0.006	0.025 ± 0.005	0.010 to 0.033	0.010 ± 0.005	0.015 ± 0.005
M55342/02	В	0.055 ± 0.006	0.050 ± 0.005	0.010 to 0.033	0.010 ± 0.005	0.015 ± 0.005
M55342/03	В	0.105 ± 0.007	0.050 ± 0.005	0.010 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/04	В	0.155 ± 0.007	0.050 ± 0.005	0.015 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/05	В	0.230 ± 0.007	0.075 ± 0.005	0.010 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/06	В	0.080 ± 0.006	0.050 ± 0.005	0.010 to 0.033	0.016 ± 0.008	0.015 ± 0.005
D55342/07	В	0.126 ± 0.008	0.063 ± 0.005	0.010 to 0.033	0.020 + 0.005/- 0.010	0.020 + 0.005/- 0.010
M55342/08	В	0.209 + 0.009/- 0.018	0.098 ± 0.005	0.010 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/09	В	0.259 + 0.009/- 0.015	0.124 ± 0.005	0.010 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/10	В	0.105 ± 0.007	0.100 ± 0.005	0.010 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/11	В	0.040 ± 0.005	0.025 ± 0.005	0.010 to 0.033	0.010 ± 0.005	0.015 ± 0.005
M55342/12	В	0.064 ± 0.006	0.032 ± 0.005	0.010 to 0.033	0.012 ± 0.005	0.015 ± 0.005

ENVIRONMENTAL TESTS				
ENVIRONMENTAL TEST	MIL-PRF-55342 LIMITS (△R ±)	VISHAY PERFORMANCE (△R ±)		
Thermal Shock	0.1 %	0.020 %		
Low Temperature Operation	0.1 %	0.025 %		
Short Time Overload	0.1 %	0.050 %		
High Temperature Exposure	0.1 %	0.009 %		
Resistance to Bonding	0.2 %	0.006 %		
Moisture Resistance	0.2 %	0.004 %		
TCR	± 25 ppm/°C	< 15 ppm/°C		
Life (2000 h at + 70 °C)	0.5 %	0.02 %		
Life (10 000 h at + 70 °C)	2.0 %	0.04 %		

MECHANICAL SPECIFICATIONS			
Resistive Element	Tantalum nitride (Ta ₂ N)		
Substrate Material	Alumina		
Chip Terminations	Solder over nickel		
Plated Solder	90/10		


FSCM CAGE # - 57489




E/H (Ta2N) (Military M/D55342)

www.vishay.com

Vishay Dale Thin Film







Legal Disclaimer Notice

Vishay

Disclaimer

ALL PRODUCT, PRODUCT SPECIFICATIONS AND DATA ARE SUBJECT TO CHANGE WITHOUT NOTICE TO IMPROVE RELIABILITY, FUNCTION OR DESIGN OR OTHERWISE.

Vishay Intertechnology, Inc., its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "Vishay"), disclaim any and all liability for any errors, inaccuracies or incompleteness contained in any datasheet or in any other disclosure relating to any product.

Vishay makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Vishay disclaims (i) any and all liability arising out of the application or use of any product, (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability.

Statements regarding the suitability of products for certain types of applications are based on Vishay's knowledge of typical requirements that are often placed on Vishay products in generic applications. Such statements are not binding statements about the suitability of products for a particular application. It is the customer's responsibility to validate that a particular product with the properties described in the product specification is suitable for use in a particular application. Parameters provided in datasheets and / or specifications may vary in different applications and performance may vary over time. All operating parameters, including typical parameters, must be validated for each customer application by the customer's technical experts. Product specifications do not expand or otherwise modify Vishay's terms and conditions of purchase, including but not limited to the warranty expressed therein.

Hyperlinks included in this datasheet may direct users to third-party websites. These links are provided as a convenience and for informational purposes only. Inclusion of these hyperlinks does not constitute an endorsement or an approval by Vishay of any of the products, services or opinions of the corporation, organization or individual associated with the third-party website. Vishay disclaims any and all liability and bears no responsibility for the accuracy, legality or content of the third-party website or for that of subsequent links.

Vishay products are not designed for use in life-saving or life-sustaining applications or any application in which the failure of the Vishay product could result in personal injury or death unless specifically qualified in writing by Vishay. Customers using or selling Vishay products not expressly indicated for use in such applications do so at their own risk. Please contact authorized Vishay personnel to obtain written terms and conditions regarding products designed for such applications.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted by this document or by any conduct of Vishay. Product names and markings noted herein may be trademarks of their respective owners.